

<b>THOMSON</b> <b>DELPHION</b>		<b>RESEARCH</b>	<b>PRODUCTS</b>	<b>INSIDE DELPHION</b>
<a href="#">Home</a>	<a href="#">My Account</a>	<a href="#">Products</a>	Search: <a href="#">Quick/Number</a> <a href="#">Boolean</a> <a href="#">Advanced</a> <a href="#">Derwent</a>	

## The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)

Tools: Add to Work File: [Create new Work File](#)

View: [INPADOC](#) | Jump to: [Top](#)

[Email this to a](#)

**Title:** JP2001307688A2: PACKING MATERIAL FOR LITHIUM ION BATTERY

**Country:** JP Japan

**Kind:** A2 Document Laid open to Public inspection I

**Inventor:** YAMASHITA RIKIYA;  
OKUSHITA MASATAKA;  
YAMADA KAZUKI;  
MIYAMA HIROSHI;

**Assignee:** DAINIPPON PRINTING CO LTD  
[News, Profiles, Stocks and More about this company](#)

**Published / Filed:** 2001-11-02 / 2000-04-19

**Application Number:** JP2000000118300

**IPC Code:** H01M 2/02; H01M 10/40;

**Priority Number:** 2000-04-19 JP2000000118300

**Abstract:** PROBLEM TO BE SOLVED: To provide a manufacturing method of a packing material for a lithium ion battery that is used as a material for packing a lithium ion battery, and that has excellent protective physical properties of the lithium ion battery main body and improved productivity in an emboss molding process or the like.


SOLUTION: This packing material for a lithium ion battery is composed of at least a base-material layer, an adhesive layer, aluminum, a conversion treatment layer and a sealant layer, and the resin constituting the sealant layer comprises 0.5 weight % to 10 weight % of one, or two and more of such agents as fluid paraffin, a fatty-acid-ester-system lubricant, a dispersing agent consisting of polyester-system surfactants, and a polyglycerin-ester-system additive. The conversion treatment is potassium chromate treatment, and the resin constituting the sealant layer is random propylene, linear low-density polyethylene and medium-density polyethylene. The sealant layer has a multilayer structure composed of two or more layers, and the innermost resin layer of the sealant layer with the multilayer structure contains the additive.

COPYRIGHT: (C)2001,JPO

**INPADOC** None **Get Now:** [Family Legal Status Report](#)

**Legal Status:** AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE TR CA  
**Designated Country:** CN EP KR US


**Family:** [Show 9 known family members](#)



Best Available Copy

Forward  
References:

Go to Result Set: Forward references (1)

PDF	Patent	Pub.Date	Inventor	Assignee	Title
	<a href="#">US6586912</a>	2003-07-01	Tsukamoto; Hisashi	Quallion LLC	Method and apparatus for amplitude limiting battery temperature spikes

Other Abstract  
Info:

CHEMABS 135(16)229378H DERABS C2001-570760



[Nominate this for the Gallery...](#)



© 1997-2004 Thomson

[Research Subscriptions](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#) | [Help](#)



(19)

(11) Publication number: **20013076**

Generated Document.

**PATENT ABSTRACTS OF JAPAN**(21) Application number: **2000118300**(51) Intl. Cl.: **H01M 2/02 H01M 10/40**(22) Application date: **19.04.00**

(30) Priority:

(43) Date of application publication: **02.11.01**

(84) Designated contracting states:

(71) Applicant: **DAINIPPON PRINTING CO L**(72) Inventor: **YAMASHITA RIKIYA  
OKUSHITA MASATAKA  
YAMADA KAZUKI  
MIYAMA HIROSHI**

(74) Representative:

**(54) PACKING MATERIAL  
FOR LITHIUM ION  
BATTERY**


(57) Abstract:

**PROBLEM TO BE SOLVED:** To provide a manufacturing method of a packing material for a lithium ion battery that is used as a material for packing a lithium ion battery, and that has excellent protective physical properties of the lithium ion battery main body and improved productivity in an emboss molding process or the like.

**SOLUTION:** This packing material for a lithium ion battery is composed of at least a base-material layer, an adhesive layer, aluminum, a conversion treatment layer and a sealant layer, and the resin constituting the sealant layer comprises 0.5 weight % to 10 weight % of one, or two and more of such agents as fluid paraffin, a fatty-acid-ester-system lubricant, a dispersing

agent consisting of polyester-system surfactants, and a polyglycerin-ester-system additive. The conversion treatment is potassium chromate treatment, and the resin constituting the sealant layer is random propylene, linear low-density polyethylene and medium-density polyethylene. The sealant layer has a multilayer structure composed of two or more layers, and the innermost resin layer of the sealant layer with the multilayer structure contains the additive.

COPYRIGHT: (C)2001,JPO



Best Available Copy

Best Available Copy